

Glasurit® HS Topcoat Hardener / HS Filler Hardener



Application:

Glasurit HS topcoat hardeners
to be mixed with Glasurit 22 Line topcoats and Glasurit 923- clears

- 929-93 RATIO System
- 929-91 quick panel repairs, low temperatures
- 929-94 very large areas, high temperatures (> 30°C)

Glasurit HS filler hardeners
to be mixed with Glasurit 285- undercoat materials

- 929-55 Glasurit HS Hardener, fast
- 929-56 Glasurit HS Hardener, normal

Remarks:

- Seal cans with left-over material carefully!
- Hardeners are sensitive to humidity!
- See Technical Information sheets for base products.

Please refer to the EU Material Safety Data Sheet for product labelling as required by Directive 1999/45/EC and the respective national rules. The products are suitable for professional use only.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. It cannot be ruled out that this product contains particles < 0.1 µm.

BASF Coatings GmbH
Automotive Refinish Coatings Solutions
Europe
Glasuritstrasse 1
48165 Münster
Germany

