

# Technical Data Sheet.

## **Permasolid® HS Optimum Plus Clear Coat 8650.**

Permasolid® HS Optimum Plus Clear Coat 8650 is a VOC-compliant high-grade High Solid clear coat.

Optimal application even under unfavourable spray booth conditions, e.g. low drying temperature.

- variable and productive application
- dries very quickly
- easy and fast to polish
- It is possible to use Permasolid® HS Accelerator 9025 / Permasolid® Additive 9026 with this clear coat

For professional use only!

VR Technical Data Sheet No. EN / 8650 / 05



## Substrate.

Suitable base coats:

Permahyd® Hi-TEC Base Coat 480  
Permahyd® Base Coat 280/285  
Permahyd® Fascination Colors and Effect Base Coats  
(see VR Technical Data Sheet No. 280, 285, 286, 480.0,  
480.1, SYS 101.3)

## Application.

Mixing ratio:



3:1 by volume with  
Permasolid® VHS Hardener 3220 fast  
Permasolid® VHS Hardener 3225  
Permasolid® VHS Hardener 3230 slow  
Permasolid® VHS Hardener 3240 extra slow

Reducer:

Permacron® Reducer 3380  
Permacron® Reducer 3385 slow  
Permasolid® HS Accelerator 9025\*\*\*  
Permasolid® Additive 9026\*\*\*

Please observe the special notes indicated by \*\*\* and the  
Technical Data Sheets of 9025 and 9026 !

Pot life:

Ready for use 45 - 60 minutes at +20°C.  
(depending on hardeners used)

Application viscosity  
4 mm, +20°C, DIN 53211:

Reducer at +20°C  
material temperature:

Spray nozzle\*:

Spray pressure\*:

Atomising pressure\*:

Number of coats:





Recommended  
film thickness:

Special notes:

## Special note:

## Drying.

Air drying:

	Compliant	HVLP
	mixing viscosity	
	10% Permacron® Reducer 3380 / 3385***	
	1.2 - 1.3 mm	1.3 - 1.4 mm
	2 - 2.5 bar	-
	-	0.7 bar
	1.5** coats	
	40 - 60 µm dry film thickness:	

\*\*\* When this clear coat is used to repair smallest damages (speed repair method), 10% Permasolid® Reducer 3380 / 3385 may be replaced by 10% Permasolid® HS Accelerator 9025 or Permasolid® Additive 9026.  
Do not use for horizontal areas.

Elastification of rigid and halfrigid types of plastic:  
First, add 15 % of Permasolid® Elastic Additive 9050 to the clear coat.

Mixed 3:1 with VHS Hardener +  
10% Permacron® Reducer 3380 or  
10% Permacron® Reducer 3385 slow

Important note: longer drying time.



At +20°C ambient temperature

dust dry:	15 - 30 minutes
dry for assembly:	2 - 5 hours
dry:	overnight

\* See manufacturer's instructions!

\*\* When applying this clear coat, the first half coat should be a light coat almost forming an opaque film. A full coat should then follow directly.

### Force drying:



Flash-off time:

5 minutes

Hardener:

VHS Hardener 3220 fast

Drying time:

10 - 15 minutes

Hardener:

VHS Hardener 3225

Drying time:

15 - 25 minutes

Hardener:

VHS Hardener 3230 slow

Drying time:

20 - 30 minutes

Hardener:

VHS Hardener  
3240 extra slow

Drying time:

25 - 35 minutes

Temperature:

at +60°C metal temperature

See Technical Data Sheet 3220 - 3240 for usage of the VHS hardeners.

### Infrared drying:



Flash-off time:

5 minutes

Drying time (depending on film thickness and hardener):

short wave:

8 - 12 minutes

### Data.

Flash point:

above +23°C

VOC content:

2004/42/IIB(d)(420)420

The EU limit value for this product (product category IIB.d) in ready to use form is max. 420 g/litre of VOC.

The VOC content of this product in ready to use form is max. 420 g/l.

---

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose.

The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed.

The intellectual property in this Information, including patents, trademarks and copyrights, is protected.  
All rights reserved.

We may modify and/or discontinue operation of all or portions of this information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

SPIES HECKER GMBH  
Horbeller Straße 17  
D-50858 Köln  
Phone ++49 (0)2234 - 6019-06  
Fax ++49 (0)2234 - 6019-4100  
[www.spieshecker.com](http://www.spieshecker.com)

Spies Hecker.  
A member of DuPont  
Performance Coatings.

