



Standohyd Basecoat

- **Water-thinnable**
- **Easy to blend in**
- **Good opacity**
- **High coverage**
- **Outstanding colour accuracy**
- **Contains less than 10% organic solvent**
- **Solid, metallic, pearl colours**



Technical Description:

- Thin with Standohyd Demineralized Water
- Use mixing stick
- 1 working spray pass

Standohyd Basecoat

Substrate:

- Standohyd 1K Primer Surfacer
- Stadox VOC / 2K Filler
- Through-hardened sanded paintwork
- Standoflex 2K Plastic Primer Surfacer
- Standoflex Plastic Filler

Do not forget cleaning!

Pretreatment / Cleaning:



For substrate preparation information see Stadox Painting System S1.



Use air fed respirator. Refer to relevant Health and Safety Data sheets.

A working pass =
1 thin coat
1 normal coat

For effect colours 1 additional light coat is possible to control metallic effect.

Flash off time can be reduced by

- Using air blower
- Spray booth blower system
- Infrared drying
- Increasing spray booth temperature

Application:




approx. 10% Standohyd Demineralized Water
22-26 s / DIN 4 mm / 20°C
61-76 s / ISO 4 mm / 20°C



Compliant 1.2 – 1.3 mm
2.0 - 2.5 bar inlet pressure
1.5 = 15 - 25 micron



HVLP 1.2 - 1.3 mm
0.7 bar atomization pressure
1.5 = 15 - 25 micron



Final flash off until matt



Standocryl VOC Clears

Standohyd Basecoat

Flash point:

- 54 - 80 °C / 129.2 – 176.0 °F

Specific Gravity:

- 1.01 - 1.19 g/cm³

Solid Content

(without thinner added):

- 16.1 - 36.8 Weight %
- 13.8 - 24.3 Volume %

VOC (2004/42/EC):

2004/42/II B(d)(420)420

The EU limit value for this product (product category: IIB.d) in ready for use form is max 420 g/litre of VOC. The VOC content of this product in ready for use form is max. 420 g/l.

Theoretical Coverage:

- 10-16 m²/l at 15 micron dry film thickness

Cleaning of equipment:

Clean after use with Standox Cleaning Thinner.

Important remarks:

- The equipment for water-thinnable products must be compatible with waterbased products.
- When collecting waste for disposal separate water-thinnable products from conventional ones, otherwise waste disposal will be more difficult and expensive, if not impossible.
- Spot repair see Standox Painting System S9.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.